

MAGNETIC CHARACTERISTICS

GRADE	Br (mT)	Br (KGs)	Hcb (KA/m)	Hcb (KOe)	Hcj (KA/m)	Hcj (KOe)	(BH)Max (KJ/m ³)	(BH)Max (MGOe)
JFI-022	102	1.02	80	1.000	183	2.300	1.6	0.20
JFI-032	134	1.34	91	1.140	159	2.000	2.8	0.35
JFI-162	260	2.60	183	2.300	231	2.900	13.1	1.60
JFI-182	272	2.72	183	2.300	223	2.800	14.3	1.80
JFI-192	280	2.80	183	2.300	215	2.700	15.1	1.90
JFI-202	292	2.92	175	2.200	199	2.500	16.5	2.10
JFI-212	298	2.98	183	2.300	215	2.700	17.1	2.15
JFI-222	304	3.04	171	2.150	187	2.350	18.5	2.30
FBP-1210	65-75	.65-.75	40-48	.503-.603	190-230	2.40-2.89	0.6-0.8	.07-0.1
FBP-1211	110-130	1.10-1.30	70-85	.880-1.068	190-230	2.40-2.89	1.5-3.0	0.19-0.38
FBP-1212	130-150	1.30-1.50	85-105	1.070-1.320	190-230	2.40-2.89	3.0-4.2	0.38-0.53
FBP-1213	210-240	2.10-2.40	120-170	1.510-2.140	160-230	2.01-2.89	7.0-12.0	0.88-1.50
FBP-1214	250-260	2.50-2.60	164-174	2.060-2.190	210-230	2.64-2.89	11.9-12.5	1.50-1.57
FBP-1215	250-260	2.50-2.60	174-184	2.190-2.310	230-280	2.89-3.52	12.1-12.7	1.52-1.60
FBP-1216	250-260	2.50-2.60	184-194	2.310-2.440	280-320	3.25-4.00	12.3-12.9	1.55-1.62
FBP-1217	270-280	2.70-2.80	170-190	2.140-2.390	210-230	2.64-2.89	14.3-14.9	1.80-1.87
FBP-1218	270-280	2.70-2.80	180-200	2.260-2.390	230-280	2.89-3.52	14.4-15.0	1.80-1.88
FBP-1219	270-280	2.70-2.80	190-200	2.390-2.510	280-320	3.52-4.00	14.5-15.1	1.82-1.89
FBP-1220	275-285	2.75-2.85	180-200	2.260-2.510	210-250	2.64-3.14	14.7-15.5	1.85-1.95
FBP-1221	285-295	2.85-2.95	190-210	2.390-2.640	210-250	2.64-3.14	15.5-17.0	1.95-2.14
FBP-1222	245-265	2.45-2.65	170-180	2.140-2.260	210-250	2.64-3.14	11.0-13.0	1.38-1.63
WT-S62	239	2.39	177	2.23	216	2.72	11.1	1.40
WT-S65	275	2.75	186	2.34	221	2.78	14.9	1.90
WT-S68	289	2.89	189	2.38	218	2.72	16.5	2.10
WT-F26S	275	2.75	187	2.35	176	2.87	15.4	1.90
WT-A27E	284	2.84	191	2.40	227	2.85	16	2.00
WT-1220KD3	288	2.88	190	2.39	229	2.88	16.5	2.10
WT-1618	260	2.60	180	2.26	195	2.45	13.5	1.70
WT-1619	280	2.80	463	2.05	178	2.24	15.1	1.90
WT-XNA3	394	3.94	241	3.04	674	8.46	25.4	3.20
WT-XNA4	424	4.24	276	3.47	716	9.00	32.4	4.10
WT-XNA5	490	4.90	338	4.25	717	9.01	39.2	4.90
WT-NAA6	527	5.27	355	4.47	725	9.11	48.6	6.10
NF04	140-160	1.4-1.6	80-104	1.000-1.300	127-191	1.60-2.40	3.18-4.78	.40-60
NF06	160-190	1.6-1.9	96-111	1.200-1.400	120-191	1.50-2.40	4.78-6.37	.60-80
NF07	190-220	1.9-2.2	104-135	1.300-1.700	160-223	2.00-2.80	6.37-7.96	.80-1.00
NF09	220-230	2.2-2.3	131-159	1.650-2.000	160-223	2.00-2.80	7.96-9.55	1.00-1.20
NF10	230-240	2.3-2.4	151-167	1.900-2.100	191-255	2.40-3.20	9.55-10.75	1.20-1.35
NF11	240-250	2.4-2.5	159-179	2.000-2.250	191-263	2.40-3.30	10.75-11.94	1.35-1.50

CONTACT IMI FOR THERMAL INFORMATION